



**HANDI-FOAM®** is a one-component moisture-cure polyurethane foam used in small holes, cracks and voids to fill, seal, bond, retrofit, insulate, stop air infiltration and deaden sound.

- ⇒ Expands 2 to 3 times extruded bead
- ⇒ Adheres to all surfaces except Teflon®, silicone, polyethylene and other plastics

**RECOMMENDED FOR:**

HEATING / AIR CONDITIONING  
PLUMBING  
REFRIGERATION  
ELECTRICAL

**DIRECTIONS:**

- ⇒ Wear impervious gloves, goggles and work clothes during use. Use with adequate ventilation.
- ⇒ Optimal temperature for use is between 65-100°F (18-38°C). Clean grease and oil off surfaces to be foamed. Cover surrounding surfaces.
- ⇒ Shake can well. Screw nozzle adapter onto valve stem, being careful not to activate valve.
- ⇒ With valve end of can down, slowly press trigger to dispense foam. Test on experimental surface.
- ⇒ Fill cavity only 1/3 full with foam to allow for expansion. For cavities greater than 3 in. (75 mm) diameter, moisten substrate before applying.
- ⇒ Dries tack-free in approximately 10 minutes, cures in 24 hours. Do not disturb uncured foam.
- ⇒ Cured foam can be trimmed or sanded. Cured foam exposed to sunlight should be covered with paint or stain.
- ⇒ Store upright in cool, dry area. Leave nozzle on can. To reuse, cut 1 in. (3 cm) off nozzle tip.
- ⇒ Uncured foam may be removed with acetone. Cured foam must be removed mechanically.
- ⇒ Read all instructions and safety information prior to use of any products.

